



817R

File Number: E116659

Yellow Card® 

COMPANY

BOSTIK SA

Zone Industrielle Le Lac
Privas, 07000 France

MODEL INFO

Thermelt: 817R

Polyamide (PA), furnished as pellets

FLAMMABILITY PROPERTIES	VALUE	TEST METHOD
Flammability (0.75 to 0.83 mm, Color: NC)	V-0	ANSI/UL 94
ISO/IEC FLAMMABILITY PROPERTIES	VALUE	TEST METHOD
Flammability (0.75 to 0.83 mm, Color: NC)	V-0	IEC 60695-11-10
THERMAL PROPERTIES	VALUE	TEST METHOD
Relative Thermal Index - Electrical Strength (0.75 to 0.83 mm)	65 °C	UL 746B

Relative Thermal Index - Mechanical Impact (0.75 to 0.83 mm)	65 °C	UL 746B
Relative Thermal Index - Mechanical Strength (0.75 to 0.83 mm)	65 °C	UL 746B

Report Date: 2014-12-03
Revision Date: 2014-12-06

The appearance of a company's name or product in this database does not in itself assure that products so identified have been manufactured under UL's Follow-Up Service. Only those products bearing the UL Mark should be considered to be Certified and covered under UL's Follow-Up Service. Always look for the Mark on the product.

UL permits the reproduction of the material contained in the Online Certification Directory subject to the following conditions: 1. The Guide Information, Assemblies, Constructions, Designs, Systems, and/or Certifications (files) must be presented in their entirety and in a non-misleading manner, without any manipulation of the data (or drawings). 2. The statement "Reprinted from the Online Certifications Directory with permission from UL" must appear adjacent to the extracted material. In addition, the reprinted material must include a copyright notice in the following format: "© 2022 UL LLC"